

DFL Dry Film Lubricant

DFL is a white, dry-film lubricant, for use where mineral oils or silicones are not suitable. It is also suitable for use as an anti-stick and mould release agent or where products of the highest purity are required. The film will not contaminate, migrate or pick up dust and dirt particles.

- Dry film lubricant; clean and non-oily
- Suitable for use on wood, plastic, fibre, metal, glass, etc.; testing advised
- Water repellent and chemically inert; suitable for a wide number of applications
- This product conforms with MIL-L-60326 (MU & MU Amendment 1)

Approvals **RoHS Compliant (2015/863/EU):** **Yes**

Typical Properties

Colour	White Translucent Fluid
Density (g/ml)	1.58
Temperature Range (°C)	-200 to +260
Mean Particle Size	5 microns
Molecular Weight	3700
Coefficient Of Friction	0.04
Softening Point (ASTM E-28-58T (°C))	265
Melting Point (Crystalline) (°C)	300
4 Ball Wear (mm)	2.568
Weld Load (kgf)	126

<u>Description</u>	<u>Packing</u>	<u>Order Code</u>	<u>Shelf Life</u>
Dry Film Lubricant	200ml aerosol	DFL200D	48 months

Directions for Use

Shake can to ensure good dispersion of ingredients and spray on to the surface to be treated from a distance of 4" to 6". When using as a release agent apply a number of thin coats rather than one thick coat to avoid cracking.

Copyright Electrolube 2013

All information is given in good faith but without warranty. Properties are given as a guide only and should not be taken as a specification.

Electrolube cannot be held responsible for the performance of its products within any application determined by the customer, who must satisfy themselves as to the suitability of the product.

Ashby Park, Coalfield Way,
Ashby de la Zouch,
Leicestershire LE65 1JR

T +44 (0)1530 419 600

F +44 (0)1530 416 640

BS EN ISO 9001:2008
Certificate No. FM 32082

Typical Product Applications

As a lubricant for leather, plastics, synthetic or natural fibres, glass, metals, wood etc.; on nuts, bolts and bearings on most machinery parts; on musical instruments, hi-fi and video equipment, computers and peripheral equipment; on metal, wood and glass in the house, e.g. door hinges, drawers, zips; on scientific apparatus, e.g. microscope slide, slide rulers, tapered glass joints; on photographic equipment, e.g. cameras, enlargers, tripods etc.

DFL can also be used as a release agent for moulded rubber and plastic items as well as injection dies and moulds. As an anti-stick agent it is highly suitable for use on freezer interiors, platens, conveyor belts, etc.

Revision 2: Jan 2019

Copyright Electrolube 2013

All information is given in good faith but without warranty. Properties are given as a guide only and should not be taken as a specification.

Electrolube cannot be held responsible for the performance of its products within any application determined by the customer, who must satisfy themselves as to the suitability of the product.

Ashby Park, Coalfield Way,
Ashby de la Zouch,
Leicestershire LE65 1JR

T +44 (0)1530 419 600

F +44 (0)1530 416 640

BS EN ISO 9001:2008
Certificate No. FM 32082